
DOOR FRAMES

Ceiling moulding 200 × 9 × 3 cm

Ceiling Moulding — polystyrene moulding, ready to install and paint.

COATED EXPANDED POLYSTYRENE | POLYSTYRÈNE | FIRE BEHAVIOUR SELF-EXTINGUISHING



IDENTIFICATION

Dartank reference	**D8ML530**
Dartank EAN	**3701839304877**
Material	**Coated expanded polystyrene**
Sales unit	**Linear metre**

OVERVIEW

Overview

A hardened expanded polystyrene core, factory-coated with a smooth polymer-quartz render that protects it and makes it ready to paint. Lightweight, it is bonded without mechanical fixing.

KEY BENEFITS

01
Lightweight
EPS core: installed by bonding alone.

02
Protected surface
Smooth, tough polymer-quartz coating.

03
Self-extinguishing
The core does not propagate flame.

04
Non-toxic
Safe material for interiors.

05
Ready to paint
Elastic water-based paint, two coats.

06
Made to measure
Profiles available on request.

PRODUCT CHARACTERISTICS

Material	**Polystyrène**

THE MATERIAL

Coated expanded polystyrene

Highly hardened expanded polystyrene core (EPS 100) protected by a smooth polymer-quartz coating: light, robust mouldings, also made to measure.

Application	**Interior**
Coating	**Smooth polymer-quartz coating**
Installation method	**Bonding**
Compatible paints	**Elastic water-based paint, two coats; silicate and solvent paints prohibited**

PERFORMANCE AND TEST RESULTS

Property	Standard	Result
Expanded polystyrene grade	EN 13163	**EPS 100**
Fire behaviour		**Self-extinguishing**
Excluded substances		**Non-toxic**

INSTALLATION

Installation

1. **Substrate** The substrate must be dry, clean, dust-free and degreased. A crumbling wall must be primed first.
2. **1. Measure and cut** Measure carefully, then cut in a mitre box with a fine-toothed saw (45° to 90° cuts). Allow about 10 % extra length for cuts.
3. **2. Sand and dry-fit** Deburr the cuts with fine sandpaper, then dry-fit the pieces to check wall contact and mitre alignment.
4. **3. Apply adhesive** Apply mounting adhesive over the whole contact surface. Also bond the joints between pieces, with jointing adhesive where the range provides one (gap of at least 1 mm).
5. **4. Press and clean** Press the piece along its full length; it can be adjusted for a few minutes. Remove excess adhesive with a spatula or damp sponge.
6. **5. Joints** Let joints dry for 24 h. Fill the wall/moulding junction with adhesive or filler, then sand. Do not use silicone sealant: it cannot be sanded or painted.
7. **6. Paint** Paint with a solvent-free water-based paint in two coats, following the paint maker's drying times. In bathrooms, choose a water-based paint suited to wet rooms.

MAINTENANCE

Care and maintenance

Routine	**No special maintenance. Dust with a broom or a vacuum cleaner fitted with a clean soft brush.**
Lacquered surfaces	**Versions with a factory lacquer finish can be cleaned with a damp cloth, water or an alcohol-free cleaner.**

QUANTITIES

VARIANTS — 12

VARIANT	REF.
Moulure de plafond D8ML509	D8ML509
Moulure de plafond D8ML510	D8ML510
Moulure de plafond D8ML523	D8ML523
Moulure de plafond D8ML525	D8ML525
Moulure de plafond D8ML527	D8ML527
Moulure de plafond D8ML529	D8ML529
Moulure de plafond D8ML531	D8ML531
Moulure de plafond D8ML511	D8ML511
Moulure de plafond D8ML512	D8ML512
Moulure de plafond D8ML513	D8ML513
Moulure de plafond D8ML514	D8ML514
Moulure de plafond D8ML515	D8ML515

WARNING

Silicate and solvent paints prohibited; primer not recommended on the coating. Cut at low speed to avoid melting the core. No silicone sealant at junctions.

Non-contractual document. Values are given for guidance; official documents are available on request.