EXOTIC TIMBER

Massaranduba grooved decking board 21×145, FAS class

Wood species: Massaranduba.

TROPICAL DECKING HARDWOOD | BOIS | EXTÉRIEUR



IDENTIFICATION

Dartank reference	**D7W130**
Dartank EAN	**3701839311042**
Material	**Tropical decking hardwood**
Thickness	**21 mm**
Sales unit	**Square metre (m²)**

OVERVIEW

Wood species: Massaranduba. Thickness: 21 mm. Width: 145mm. Length: on request. Class: FAS. Profile: Ryflowany. Protection method: None. Price for: 1 m² gross.

PRODUCT CHARACTERISTICS

Material	**Bois**
Width	**145 mm**
Profile	**Rainuré**
Application	**Extérieur**
Length	**sur demande**
Protection	**Aucune**
Wood species	**Massaranduba**
Class	**FAS**

THE MATERIAL

Tropical decking hardwood

Other FAS-grade tropical hardwoods for decking and joists.

Appearance grades	**FAS / FAS KD**

INSTALLATION

Installation

1. **Substructure** Install above ground with sufficient ventilation.
2. **Gap between boards** Leave about 4–7 mm between boards (more for the most reactive species).
3. **End gap** Allow about 2–3 mm between board ends.
4. **Screwing** Screws twice as long as the board is thick, driven at 90°, head flush (neither proud nor sunk).
5. **Pre-drilling** Always pre-drill, even with self-drilling decking screws.
6. **Fasteners** A2 stainless-steel screws for tropical hardwoods and larch.
7. **Pre-installation check** Starting installation means accepting the product's condition: report any defect before cutting, drilling or treating.
8. **Workmanship** Installation should be carried out by a professional in line with good building practice.

Storage

- **Stacking** Stack boards flat, strapped and/or evenly weighted, allowing air to circulate.
- **Shelter** Store in a dry place protected from water and UV.
- **Stacking** Unsecured storage risks cupping and twisting.

QUANTITIES

COVERAGE PER M² — 8% cutting waste

AREA	BILLED
5 m²	5.4 m²
10 m²	10.8 m²
20 m²	21.6 m²
50 m²	54 m²

Non-contractual document. Values are given for guidance; official documents are available on request.